

# **Molykote<sup>®</sup> D-321 R Anti-friction Coating**

## **FEATURES & BENEFITS**

- Air drying
- Avoidance of stick-slip
- High aging resistance

## **COMPOSITION**

- Solid lubricants
- Solvents
- Binder

Air-curing dry lubricant

## **APPLICATIONS**

- For metal/metal combinations with slow to medium fast movements and high loads.
- Suitable for the permanent lubrication of highly stressed sliding guides with low sliding speeds, oscillating movements or intermittent operation.
- Improving the running-in process and for lubrication under high vacuum and at extreme temperatures.
- Used successfully for cylinder-head bolts, toaster guides, car mirror adjustment mechanisms, high voltage switches, for the running-in of highly stressed gear wheel.
- Emergency lubricant for parts of the rotor head of wind energy installations and for groove-free cold extrusion of steel.

## **TYPICAL PROPERTIES**

Specification Writers: These values are not intended for use in preparing specifications. Please contact your local Dow Corning sales office or your Global Dow Corning Connection before writing specifications on this product.

<b>Test*</b>	<b>Property</b>	<b>Unit</b>	<b>Result</b>
	Color		Grey-black
	<b>Physical Properties</b>		
DIN 53211/3	Viscosity at 25°C (DIN3 cup)	seconds	23
DIN 53217/2	Density at 20°C	g/ml	1.07
CTM 0242 I	Nonvolatile content	%	29
	Storage life	months	24
	<b>Temperature</b>		
	Drying time	min/°C	5/23
	Service temperature range	°C	-180 to +260
	<b>Load-carrying capacity, wear protection, service life</b>		
ASTM-D2625	Falex load-carrying capacity <sup>1</sup>	N	b=4500 p=12500 s=6800 b=212
ASTM-D2714	LFW-I, rotating <sup>1</sup> F=2860N, n=72 minutes <sup>1</sup> , v=7.9m/minute		p=146 s=306
ASTM-D2714	LFW-1 oscillating <sup>1</sup> F=900N, frequency = 89.5osc./minute		b=178 p=400 s=362
	<b>Coefficient of friction</b>		
	Press-Fit test, $\mu$ =		0.075

\*DIN: Deutsche Industrie Norm.

CTM: Corporate Test Method, copies of CTMs are available on request.

ASTM: American Society for Testing and Materials.

<sup>1</sup>Surface pretreatment: b = blank, p = phosphated, s = sand blasted

## HOW TO USE

### Surface preparation

First clean and degrease the surface which will be coated with *Molykote*<sup>®</sup> D-321 R Anti-friction Coating. Phosphatization or sandblasting (180 grit) increases the adhesion and service life.

### How to apply

Stir *Molykote* D-321 R Anti-friction Coating thoroughly before applying by spraying or brushing. Recommended dry film thickness: 5 to 20µm.

### Drying Time

5 minutes at 23°C.

### Solubility

Thinning can be carried out using *Molykote*<sup>®</sup> L 13 Thinner.

## HANDLING

### PRECAUTIONS

**PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND MATERIAL SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE MATERIAL SAFETY DATA SHEET IS AVAILABLE ON THE DOW CORNING WEBSITE AT DOW CORNING.COM, OR FROM YOUR DOW CORNING SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CORNING CUSTOMER SERVICE.**

### USABLE LIFE AND STORAGE

When stored at or below 20°C in the original unopened containers, *Molykote* D-321 R Anti-friction Coating has a usable life of 24 months from the date of production.

## PACKAGING INFORMATION

This product is available in different standard container sizes. Detailed container size information should be obtained from your nearest Dow Corning sales office or Dow Corning distributor.

## LIMITATIONS

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

## HEALTH AND ENVIRONMENTAL INFORMATION

To support Customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area.

For further information, please see our website, [dowcorning.com](http://dowcorning.com) or consult your local Dow Corning representative.

## LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

**DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.**

**DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.**

*We help you invent the future.*<sup>TM</sup>

[molykote.com](http://molykote.com)